

Technical data sheet in accordance with ASTM

Material

NBR NB903406

black

cross linking: sulfur

revision index

2

revision date

7/3/2017

page

1 / 3

Physical properties

	nominal range	typical values	
Density ASTM D 1817, 23 °C	1.32 ±0.02	1.32	g/cm ³
Hardness ASTM D2240, Shore A, 23 °C	90 ±5	90	Shore
Tensile strength ASTM D412	---	16.8	MPa
Elongation at break ASTM D412	---	142	%
Low temperature test ASTM D1329, TR10	---	-30	°C
Tear strength ASTM D 624, C, 23 °C	---	50	KN/m
Compression set ASTM D395, Slab B, 22 h, 100 °C	---	6	%
Temperature range	-35°C to 100°C		

Declarations of conformity

This overview is purely informative and does not constitute a declaration of conformity (DoC). Please refer to the actual declaration of conformity (DoC) including the conditions and its validity period.

	Country	Part	Remark	Expires
RoHS conform			including EU 2011/65 and EU2015/863 (ROHS III)	see DoC

Change after aging in Air: 70h/100°C

		Typ. values		
		Base value	After aging	difference
Hardness (ASTM D2240, Shore A)	Shore	90	93	3
Tensile strength (ASTM D412)	MPa	16.8	16	-5 %
Elongation at break (ASTM D412)	%	142	110.8	-22 %
volume change (ASTM D471)	%		-2	

Freudenberg

Freudenberg Industrial Services GmbH
 Global Material Technology
 Nadja Güldner
 Telefon: -
 Fax: -
 Email: FIS.Compound.CRC@fst.com

Technical data sheet in accordance with ASTM

Material

NBR NB903406

black

cross linking: sulfur

revision index

2

revision date

7/3/2017

page 2 / 3

Change after aging in IRM 901: 70h/100°C

Hardness (ASTM D2240, Shore A)
Tensile strength (ASTM D412)
Elongation at break (ASTM D412)
volume change (ASTM D471)

Shore
MPa
%
%

Typ. values			
Base value	After aging	difference	
90	94	4	
16.8	15.5	-8 %	
142	116.4	-18 %	
	-5		

Change after aging in IRM 903: 70h/100°C

Hardness (ASTM D2240, Shore A)
Tensile strength (ASTM D412)
Elongation at break (ASTM D412)
volume change (ASTM D471)

Shore
MPa
%
%

Typ. values			
Base value	After aging	difference	
90	88	-2	
16.8	17.3	3 %	
142	125	-12 %	
	4		

Change after aging in Water: 70h/100°C

Hardness (ASTM D2240, Shore A)
Tensile strength (ASTM D412)
Elongation at break (ASTM D412)
volume change (ASTM D471)

Shore
MPa
%
%

Typ. values			
Base value	After aging	difference	
90	90	0	
16.8	17.1	2 %	
142	127.8	-10 %	
	3		

Freudenberg

Freudenberg Industrial Services GmbH
Global Material Technology
Nadja Güldner
Telefon: -
Fax: -
Email: FIS.Compound.CRC@fst.com

Technical data sheet in accordance with ASTM

Material

NBR NB903406

black

cross linking: sulfur

revision index

2

revision date

7/3/2017

page 3 / 3

No ASTM D2000 properties available

The given values are based on a limited number of tests on standard test pieces (2mm sheets). The data from finished parts can deviate from above values depending on the manufacturing process and the component geometry.

The data represents our present empirical values. It is incumbent on the person placing the order to examine whether it is suitable for its intended purpose, before using the product. All questions regarding the guarantee of this product are in line with our terms and conditions, inasmuch as statutory provisions do not plan for something else.

Freudenberg

Freudenberg Industrial Services GmbH
Global Material Technology
Nadja Güldner
Telefon: -
Fax: -
Email: FIS.Compound.CRC@fst.com