

COPPER PHOSPHOROUS BRAZING ALLOY

#item	EAN	Dimensions
867840	3660338217555	Ø 2 MM x 36 Units



Description

Higher fluidity, specially made for strong brazing of fitting, pipes and Fit up, with average joint gaps. Its higher Phosphorus content makes it more fluid. Alloy with self-fluxing properties. The corrosion resistance this alloy is comparable to that of copper excepts when the joint is exposed to sulphuric containing gas or at elevated temperatures as in a cooking range. Under these conditions, it is expected that, this alloy will undergo progressive deterioration as other copper phosphorus alloy with Silver or without silver.

General applications

Joining copper to copper it is act as self-fluxing alloy and does not required additional flux. It can be used on cuprous alloys (bronze, brass) with flux, electrical industry, plumbing trade. This brazing alloy is not recommended to be used for the media having sulphur. Also it is not allowed to use for joining steels (Fe) or materials containing Iron (Fe), Nickel (Ni), Cobalt (Co) as it will form brittle phase in the joint. In Air conditioning and refrigeration application, it can be used for the service temperature between +150°C (without loss in strength) up to -20°C. This alloy can be used for flame...Maximum short service joint operating temperature 200°C.

Specifications

Alloy	Working Temperature (°C)	NF EN ISO 17672	AWS A-5.8	DIN 8513
Cu-P	730	CuP 180		L-Cu P7

Typical Chemical Compositions (%)

Cu	P	Al	Bi	Cd	Pb	Zn	Zn + Cd	Max. impurities
Reminder	7.00	<0.01	<0.030	<0.01	<0.025	<0.050	<0.05	<0.25

Typical Physical Properties

Colour	Solidus (°C)	Liquidus (°C)	Density g/cm³	Elongation %	Tensile strength (MPa)	Electrical Conductivity (%IACS)	Electrical Resistivity (Micro-ohm-cm)
Copper	710	805	8.0	4%	450	7.48	23.05