

Material 42 CR 764

black

cross linking: Metallic oxide

revision index
6

revision date
12/21/2011

page 1 / 3

Physical properties

	nominal range	typical values	
Density DIN EN ISO 1183-1	1.37 ±0.02	1.37	g/cm ³
Hardness DIN ISO 7619-1	42 ±5	42	Shore
Rebound resilience DIN 53512	---	46	%
Modulus 100 %, DIN 53504, S2	> 0.7	1.5	MPa
Tensile strength DIN 53504, S2	> 12	15	MPa
Elongation at break DIN 53504, S2	> 300	400	%
Compression set DIN ISO 815, 22 h, 100 °C	< 35	26	%

Temperature range -40°C to 100°C

Declarations of conformity

	Country	Part	Remark	Expires	unlimited
RoHS conform			including EU 2011/65 and EU2015/863 (ROHS III)		☒

Freudenberg

Freudenberg FST GmbH
Global Material Technology
Wolfgang Becker
Telefon: +49 (0)6201/80-2893
Fax: +49 (0)6201/88-2893
Email: wolfgang.becker@FST.com

Material 42 CR 764

black

cross linking: Metallic oxide

revision index

6

revision date

12/21/2011

page 2 / 3

Tested after ASTM D 2000: M 2 BC 410 A14 B14 EO14 EO34 F17 G21

		nominal range	typical values
Hardness	Shore	40 ±5	42
Tensile strength	MPa	min. 10	12.5
Elongation at break	%	min. 500	690
A14 Change after aging in Air 70h/100°C			
Hardness	Shore	15	1
Tensile strength	%	-15	-10
Elongation at break	%	-40	-7
B14 Compression set 22h/100°C			
	%	35	23
EO14 Change after aging in IRM 901 70h/100°C			
Hardness	Shore	±10	2
Tensile strength	%	-30	-18
Elongation at break	%	-30	-19
Volume	%	-10 to 15	-3
EO34 Change after aging in IRM 903 70h/100°C			
Tensile strength	%	-70	-60
Elongation at break	%	-55	-50
Volume	%	120	70
F17 Low-temperature resistance after 3 min at -40 °C 3min./-40°C			
	°C	pass	
G21 Tear Resistance >= 10 MPa 23°C			
	MPa	26	29

The material possess an excellent ozone and weather resistance. The diesel fuel- and mineral oil resistance are sufficient.

This material contains a SVHC-substance <0,1%. (Imidazolidin-2-thion CAS-No. 96-45-7) in the vulcanized parts.

Freudenberg

Freudenberg FST GmbH
Global Material Technology
Wolfgang Becker
Telefon: +49 (0)6201/80-2893
Fax: +49 (0)6201/88-2893
Email: wolfgang.becker@FST.com

Material

42 CR 764

black

cross linking: Metallic oxide

revision index	revision date	page
6	12/21/2011	3 / 3

The given values are based on a limited number of tests on standard test pieces (2mm sheets) produced in the laboratory. The data from finished parts can deviate from above values depending on the manufactories process and the component geometry.

The data represents our present empirical values. It is incumbent on the person placing the order to examine whether it is suitable for its intended purpose, before using the product. All questions regarding the guarantee of this product are in line with our terms and conditions, inasmuch as statutory provisons do not plan for something else.

Freudenberg

Freudenberg FST GmbH
Global Material Technology
Wolfgang Becker

Telefon: +49 (0)6201/80-2893

Fax: +49 (0)6201/88-2893

Email: wolfgang.becker@FST.com