

### ALL-PURPOSE ADHESIVE White neoprene adhesive

Item #	EAN	Product
715839	3660338005466	ALL-PURPOSE ADHESIVE White neoprene adhesive

#### Product description

ALL-PURPOSE ADHESIVE White neoprene adhesive is a ready to use, solvented construction adhesive based on synthetic rubber.

Basis	SBR rubber
Consistency	Paste
Curing system	Physical drying and crystallisation
Curing speed *	Hand tight in 20 min.
Density	1,20 g/ml
Open time (*)	15 min.
Temperature resistance**	-20 °C → 60 °C
Application temperature	5 °C → 25 °C

\* These values may vary depending on environmental factors such as temperature, moisture, and type of substrates. \*\* This information relates to fully cured product.



#### Application method

Apply the adhesive by means of a caulking gun in equal beads or dots, not too thin, every 15 cm and on one of the materials that have to be glued. Always apply adhesive to the edges and corners. Press both parts together, immediately pull loose and let dry for 10-15 minutes. Afterwards bond again and batten with a rubber hammer. Support if necessary.

*Repair:* With the same material.

#### Properties

- Direct application onto one substrate with a caulking gun
- Universal use
- Suitable for bonding on uneven surfaces.
- Makes the use of screws and nails redundant.
- Water resistant
- Suitable for bonding polystyrene

#### Applications

- All bonding in assembly techniques.
- Bonding in the renovation industry.
- Bonding in construction industry.
- Bonding of cable trays and panels.

#### Packaging

Colour:

→ White

Carton : 12 units

Pallet : 1 440 units

Packaging: 310 ml cartridge

### **Shelf Life**

12 months in unopened packaging in a cool and dry storage place at temperatures between +5°C and +25°C.

### **Health- and Safety Recommendations**

Take the usual labour hygiene into account.

Use only in well-ventilated areas. Do not smoke. In case of insufficient ventilation it is appropriate to wear respiratory protection.

Consult label and material safety data sheet for more information.

### **Remarks**

→ The applied pressure and not the duration of the compression will determine the ultimate strength of the bond.

### **Substrates**

*Nature:* clean, free of dust and grease.

*Surface preparation:* No pretreatment required.

Has a good bonding on all surfaces except for PE and PP.

We recommend a preliminary adhesion test on any substrate.