

Technical data sheet in accordance with ASTM

Material

NBR NB703413

green

cross linking: sulfur

revision index

2

revision date

7/3/2017

page

1 / 3

Physical properties

	nominal range	typical values	
Density ASTM D 1817	1.46 ±0.02	1.46	g/cm ³
Hardness ASTM D2240, Shore A, 23 °C	70 ±5	70	Shore
Tensile strength ASTM D412	---	14.4	MPa
Elongation at Break ASTM D412	---	453	%
Tear strength ASTM D 624, C, 23 °C	---	61	KN/m
Compression set ASTM D395, B, 22 h, 100 °C	---	11	%
Temperature range	-40°C to 100°C		

Declarations of conformity

	Country	Part	Remark	Expires	unlimited
RoHS conform			including EU 2011/65 and EU2015/863 (ROHS III)		☒

Change after aging

in Air: 70h/100°C

		Typ. values		
		Base value	After aging	difference
Hardness (ASTM D2240, Shore A, 23 °C)	Shore	70	76	6
Tensile strength (ASTM D412)	MPa	14.4	15.4	7 %
Elongation at Break (ASTM D412)	%	453	303.5	-33 %
volume change (ASTM D471)	%		-4	

Change after aging

in Fuel A: 70h/23°C

		Typ. values		
		Base value	After aging	difference
Hardness (ASTM D2240, Shore A, 23 °C)	Shore	70	72	2
Tensile strength (ASTM D412)	MPa	14.4	13.4	-7 %
Elongation at Break (ASTM D412)	%	453	371.5	-18 %
volume change (ASTM D471)	%		0	

Freudenberg

Dichtomatik Vertriebsgesellschaft für Technische Dichtungen mbH

Global Material Technology

Nadja Güldner

Telefon: +49 40 66989 279

Fax: +49 40 66989 9279

Email: nadja.gueldner@dichtomatik.de

Technical data sheet in accordance with ASTM

Material

NBR NB703413

green

cross linking: sulfur

revision index

2

revision date

7/3/2017

page 2 / 3

Change after aging in Fuel B: 70h/23°C

Hardness (ASTM D2240, Shore A, 23 °C)
 Tensile strength (ASTM D412)
 Elongation at Break (ASTM D412)
 volume change (ASTM D471)

Shore
 MPa
 %
 %

Typ. values			
Base value	After aging	difference	
70	61	-9	
14.4	10.7	-26 %	
453	299	-34 %	
	19		

Change after aging in IRM 901: 70h/100°C

Hardness (ASTM D2240, Shore A, 23 °C)
 Tensile strength (ASTM D412)
 Elongation at Break (ASTM D412)
 volume change (ASTM D471)

Shore
 MPa
 %
 %

Typ. values			
Base value	After aging	difference	
70	73	3	
14.4	14.5	1 %	
453	317.1	-30 %	
	-4		

Change after aging in IRM 903: 70h/100°C

Hardness (ASTM D2240, Shore A, 23 °C)
 Tensile strength (ASTM D412)
 Elongation at Break (ASTM D412)
 volume change (ASTM D471)

Shore
 MPa
 %
 %

Typ. values			
Base value	After aging	difference	
70	70	0	
14.4	14.4	0 %	
453	330.7	-27 %	
	4		

Freudenberg

Dichtomatik Vertriebsgesellschaft für Technische Dichtungen mbH
 Global Material Technology
 Nadja Güldner
 Telefon: +49 40 66989 279
 Fax: +49 40 66989 9279
 Email: nadja.gueldner@dichtomatik.de

Technical data sheet in accordance with ASTM

Material **NBR NB703413**

green

cross linking: sulfur

revision index

2

revision date

7/3/2017

page 3 / 3

No ASTM D2000 properties available

The given values are based on a limited number of tests on standard test pieces (2mm sheets). The data from finished parts can deviate from above values depending on the manufacturing process and the component geometry.

The data represents our present empirical values. It is incumbent on the person placing the order to examine whether it is suitable for its intended purpose, before using the product. All questions regarding the guarantee of this product are in line with our terms and conditions, inasmuch as statutory provisions do not plan for something else.

Freudenberg

Dichtomatik Vertriebsgesellschaft für Technische Dichtungen mbH

Global Material Technology

Nadja Güldner

Telefon: +49 40 66989 279

Fax: +49 40 66989 9279

Email: nadja.gueldner@dichtomatik.de